



M24300

LINEAR LOW DENSITY POLYETHYLENE HIGH FLOW GRADE

M 24300 is a butene comonomer based Linear Low Density grade with narrow molecular weight distribution and optimum levels of antioxidants. It offers good fluidity and excellent processability, and is mainly recommended for preparing masterbatch. It can be also used for producing injection moulded lids, containers, houseware & general purpose articles as this grade exhibits good flexibility and low warpage.

Typical Characteristics*			
Property	Test Method	Unit	Typical Value**
Density (23°C)	ASTM D 1505	g/cc	0.924
MFI (190°C/2.16 Kg)	ASTM D 1238	g/10 min	30
Tensile Yield Strength	ASTM D638	MPa	10.5
Elongation at Break	ASTM D638	%	700
Flexural Modulus	ASTM D790	MPa	325
ESCR, F ₀	ASTM D 1693/B	hr	3
Softening Point	ASTM D 1525	°C	95

*Typical Characteristics and not to be taken as specifications

**Mechanical Properties are on Injection Moulded Specimen

Applications

Masterbatches, shopping baskets, lids.

Regulatory Information

- Meets the requirements stipulated in standard IS : 10146-1982 on "Specification for Polyethylene for safe use in contact with foodstuffs, pharmaceuticals, and drinking water". It also conforms to the positive list of constituents as prescribed in IS : 10141-1982. The grade and the additives incorporated in it also comply with the FDA:CFR Title 21, 177.1520, Olefin polymers.

Storage Recommendations

- Bags should be stored in dry / closed conditions at temperatures below 50°C and protected from UV / direct sunlight.

Reliance Industries Limited, Polymer Research and Technology Centre,
Swastik Mill Compound, V.N. Purav Marg, Chembur, Mumbai-400 071. Tel.: +91-22-6767 7000. E-mail: polymer_patsupport@ril.com Website: www.ril.com

• The information and data presented herein is true and accurate to the best of our knowledge. No warranty or guarantee expressed or implied, is made regarding performance or otherwise. This information and data may not be considered as a suggestion to use our products without taking into account existing patents, or legal provisions or regulations, whether national or international. • The user of any information and/or data is advised to obtain the latest details from any of the offices of the company or its authorised agents, as the information and/or data is subject to change based on the research and development work undertaken by the company.

Updated as of May, 2007